

# TECHNICAL DATA SHEET

## DX1046 NEW

### 2K VOC APPEARANCE CLEAR

**DUXONE**<sup>®</sup>  
AUTOMOTIVE PAINT SYSTEMS



#### DESCRIPTION

DX1046 NEW 2K VOC Appearance Clear is part of the Duxone repair system. This VOC compliant clear combines very easy application with excellent appearance and durability.

#### FEATURES

- Excellent mar, chemical and weather resistance.
- Suitable for spot, panel and overall repairs.
- Dries very quickly.
- VOC compliant.
- Improved control on vertical substrates.

#### PRODUCT LIST

- DX1046 NEW 2K VOC Appearance Clear
- DX1026 VOC Standard Activator
- DX32 Thinner Fast
- DX34 Thinner Standard
- DX36 Thinner Slow

# TECHNICAL DATA SHEET

## DX1046 NEW


### 2K VOC APPEARANCE CLEAR

**DUXONE**<sup>®</sup>  
AUTOMOTIVE PAINT SYSTEMS

#### Product preparation - application STANDARD



It is strongly recommended to use appropriate personal protection equipment during application to avoid respiratory, skin and eye irritation.



Duxone Basecoat / Duxone Waterborne Basecoat: Surfaces must be dried / flashed-off in accordance with TDS before application  
Existing finishes: Surfaces must be sanded and degreased before application



	Spot & panel repair		Standard		Large surface	
	Volume	Weight	Volume	Weight	Volume	Weight
<b>DX1046</b>	2	100	2	100	2	100
<b>DX1026</b>	1	53	1	53	1	53
<b>DX32</b>	4 %	6	-	-	-	-
<b>DX34</b>	-	-	4 %	6	-	-
<b>DX36</b>	-	-	-	-	4 %	6



Pot life at 20°C: 1 hr



	Spray nozzle	Spray pressure	
<b>Compliant</b>	1.3 - 1.4	1.8 - 2.2 bar	inlet pressure
<b>HVLP</b>	1.3 - 1.4	0.7 bar	atomisation pressure

see manufacturer's instructions



2 coats

with intermediate flash-off: 5 min - 10 min  
final flash-off: 0 min - 5 min



	<b>DX1026</b>
<b>20 °C</b>	6 hr
<b>60 - 65 °C</b>	30 min



Guideline for short wave IR equipment  
Half power: 5 min  
Full power: 10 - 15 min

VOC compliant

2004/42/IIB(d)(420) 420: The EU limit value for this product (product category: IIB(d)) in ready to use form is maximum 420 g/l of VOC. The VOC content of this product in ready to use form is maximum 420 g/l.

# TECHNICAL DATA SHEET

DX1046 NEW

2K VOC APPEARANCE CLEAR

**DUXONE**<sup>®</sup>  
AUTOMOTIVE PAINT SYSTEMS

## Products

DX1046 NEW 2K VOC Appearance Clear


DX1026 VOC Standard Activator

DX32 Thinner Fast


DX34 Thinner Standard

DX36 Thinner Slow

## Product mix



Mixing ratios with special agents are available in the productmix table on Colour Room and in the specific TDS.



ISO 4: 49 - 61 s at 20°C  
DIN 4: 19 - 22 s at 20°C




50 - 60 µm

### Theoretical coverage

475 - 480 m<sup>2</sup>/l at 1 micron dry film thickness

Due to different activator characteristics and different mixing ratios of the ready-to-use mixture in some TDS versions, the theoretical coverage calculation may vary.

Note: The practical material consumption depends on several factors, e.g. geometry of the object, surface formation, application method, spray gun setting, inlet pressure, etc.



DX1046 NEW 2K VOC Appearance Clear can be overcoated with itself within 24 hours, without intermediate sanding



Clean after use with a suitable solventbased guncleaner.

## Remarks

- Material has to be at room temperature (18-25°C) before use.
- Allow additional time for preheating up to panel temperature.
- Surplus ready for use material should not be returned to original can.
- Close can of clear and activator tightly immediately after use, as both products will react with humid air and water and lose their hardening effect.

# TECHNICAL DATA SHEET

DX1046 NEW

2K VOC APPEARANCE CLEAR

**DUXONE**<sup>®</sup>  
AUTOMOTIVE PAINT SYSTEMS



Consult Safety Data Sheet prior to use. Observe the precautionary notices displayed on the container.

All other products referred to in the refinish build up are from our Duxone product range. System properties will not be valid when the related material is used in combination with any other materials or additives which are not part of our Duxone product range, unless explicitly indicated otherwise.

For professional use only! The information provided in this documentation has been carefully selected and arranged by us. It is based upon our best knowledge on the subject at the date of issuance. The Information is given for information purposes only. We are not liable for its correctness, accuracy and completeness. It is up to the user to check the information with regard to up-to-dateness and suitability for his intended purpose. The intellectual property in this Information, including patents, trademarks and copyrights, is protected. All rights reserved. The relevant Material Safety Data Sheet and Warnings displayed on the product label need to be observed. We may modify and/ or discontinue operation of all or portions of this Information at any time in our sole discretion, without notice and assume no responsibility to update the Information. All rules set forth in this clause shall apply accordingly for any future changes and amendments.